

S-9016.B9

Type : Basic

Conformances

AWS A5.5/ ASME SFA5.5 E9016-B91

JIS Z3223 E6216-9C1MV

EN 1599 - ECrMo91 B 3 2 H5


Applications

- Heat resistant steel (9%Cr-1%Mo)

Features

- Good creep resistance at high temperature
- Maximum service temperature at 650°C (1202°F)
- Low-Hydrogen electrode (HDM ≤5ml/100g)

Welding Position



Current

AC, DC ±

Redrying Conditions

350~400°C (662~752°F) X
0.5~1hr

Diameter / Packaging

Diameter	Length	Standard		Vacuum				P.V.C	
		packet	carton	packet	carton	packet	carton	packet	carton
mm (in)	mm (in)	5kg(11lbs)	20kg(44lbs)	1.5kg(3.3lbs)	15kg(3.3lbs)	5kg(11lbs)	20kg(44lbs)	5kg(11lbs)	20kg(44lbs)
2.6 (3/32)	350 (14)		√		√		√		√
3.2 (1/8)	350 (14)		√		√		√		√
4.0 (5/32)	350 (14)		√		√		√		√
	400 (16)		√		√		√		√
5.0 (3/16)	400 (16)		√		√		√		√

SM/AW

SAW

GM/AW

GT/AW

FC/AW

Non-FERROUS

APPENDIX

Typical Chemical Composition of All-Weld Metal (%)

C	Si	Mn	P	S	Cr	Ni	Mo	V	Nb	N
0.10	0.24	1.00	0.009	0.006	9.07	0.45	1.00	0.22	0.036	0.035

Typical Mechanical Properties of All-Weld Metal

YS MPa(lbs/in ²)	TS MPa(lbs/in ²)	EL (%)	Temp °C(°F)	CVN-Impact Value J (ft-lbs)	Heat Treatment
660 (95,700)	762 (110,500)	24.8	20 (68)	71 (52)	760°C(1400°F) X 2hr. S.R

Typical Welding Parameters / Amp.(A)

Diameter mm (in)	2.6 (3/32)	3.2 (1/8)	4.0 (5/32)		5.0 (3/16)
Length mm (in)	350 (14)	350 (14)	350 (14)	400 (16)	400 (16)
F & HF	80~110	110~150	150~200	150~200	190~240
V-up, OH	70~100	100~140	140~200	140~200	-