

SC-80MR

Type : Metal-Cored



Conformances

AWS A5.36/ ASME SFA5.36 E80T15-M21A8-G
 (AWS A5.28/ ASME SFA5.28 E80C-G)
 EN ISO 17632-A-T 50 6 1.5Ni M M21 2 H5

DNV-GL VY40MS H5
 CE


Applications

- Offshore structure
- Heavy equipment
- General fabrication

Features

- Suitable for root-pass and multipass welding
- Good impact value at low temperature
- Low spatter
- Good anti-porosity

Welding Position



Current

DC +

Shielding Gas

Ar + 20~25% CO₂

Diameter / Packaging

Diameter	Spool			Pac		
	5kg (11lbs)	15kg (33lbs)	20kg (44lbs)	250kg (551lbs)	300kg (661lbs)	350kg (771lbs)
1.2 (0.045)	√	√	√	√	√	√
1.4 (0.052)	√	√	√	√	√	√

Typical Chemical Composition of All-Weld Metal (%)

C	Si	Mn	P	S	Ni
0.07	0.35	1.55	0.014	0.007	1.55

Typical Mechanical Properties of All-Weld Metal

YS MPa(lbs/in ²)	TS MPa(lbs/in ²)	EL (%)	Temp °C(°F)	CVN-Impact Value J (ft.-lbs)
612 (88,700)	658 (95,400)	25.5	-60 (-76)	88 (65)

Typical Welding Parameters

Diameter, Polarity Shielding Gas	CTWD mm (in)	Wire Feed Speed m/min (in/min)	Amp. (A)	Volt. (V)	Deposition Rate kg/hr (lb/hr)	Efficiency (%)
1.2mm (0.045 in) DC+						
Flat & Horizontal						
80% Ar + 20% CO ₂	19-25 (3/4-1)	7.8 (307)	240~260	22~26	3.5 (7.5)	90~96
		9.4 (374)	270~290	22~27	4.0 (9.2)	
		10.3 (405)	300~320	23~27	4.5 (10.8)	
1.4mm (0.052 in) DC+						
Flat & Horizontal						
80% Ar + 20% CO ₂	19-25 (3/4-1)	7.2 (283)	280~300	24~28	4.1 (8.9)	94~98
		7.7 (303)	310~330	26~29	4.9 (10.8)	
		10.9 (410)	350~370	27~30	6.6 (14.2)	

SWAW

SAW

GMAW

GTAW

FCAW

Non-FERROUS

APPENDIX